



TECHNOVINYL POLYMERS(I)LTD.
30, Unique Indl. Estate, Dr. Rajendra Prasad
Road, Mulund(W), Mumbai-400 080
Tel.: 022-25930940/41/43/44. Fax: 022-25642577
Email: kk_group@vsnl.net Website: www.kkthelittlegiant.com



TECHNICAL DATA SHEET

K-FLEX PVC ELASTOMER ELASOMERIC MATT FINISH WIRE & CABLE JACKETING COMPOUND

PROPERTIES	UNITS	PRODUCT CODE NO.			
		3340	3350	3360	3370
HARDNESS	Shore A	40 (±5)	50 (±5)	60 (±5)	70 (±5)
TENSILE STRENGTH	kg/cm ²	40	52	63	70
DENSITY	-	1.18	1.19	1.20	1.22
ELONGATION	%	> 400	380	316	280
COLOR	-	Natural			
OZONE RESISTANCE	-	Excellent			
USAGE TEMP.	°C	-25 to +100	-25 to +100	-25 to +100	-25 to +100

Features:

- Gel Free Extrusion
- Rubber Looks & Rubber Feel
- Matt Finish
- Good Abrasion Resistance
- Very Good Flexibility
- Soft Touch

Manufactures Of :

Thermoplastic Elastomers
Hi Performance PVC Compounds
PP Compounds
Speciality Polymers



TECHNOVINYL POLYMERS(I)LTD.
30, Unique Indl.Estate, Dr.Rajendra Prasad
Road, Mulund(W), Mumbai-400 080
Tel.: 022-25930940/41/43/44. Fax: 022-25642577
Email: kk_group@vsnl.net Website: www.kkthelittlegiant.com



TECHNICAL DATA SHEET

K-FLEX PVC ELASTOMER OIL RESISTANT ELASOMERIC MATT FINISH WIRE & CABLE JACKETING COMPOUND

PROPERTIES	UNITS	PRODUCT CODE NO.			
		3340 OR	3350 OR	3360 OR	3370 OR
HARDNESS	Shore A	40 (±5)	50 (±5)	60 (±5)	70 (±5)
TENSILE STRENGTH	kg/cm ²	48	57	69	77
DENSITY	-	1.17	1.18	1.19	1.20
ELONGATION	%	430	400	340	320
COLOR	-	Natural			
OZONE RESISTANCE	-	Excellent			
USAGE TEMP.	°C	-25 to +100	-25 to +100	-25 to +100	-25 to +100

Features:

- Oil Resistant
- Gel Free Extrusion
- Rubber Looks & Rubber Feel
- Matt Finish
- Good Abrasion Resistance
- Very Good Flexibility
- Soft Touch

Manufactures Of :

Thermoplastic Elastomers
Hi Performance PVC Compounds
PP Compounds
Speciality Polymers